

HABA Alu35

Grinded rolled aluminium plates
cut to size

Alu35 is a low-tension annealed rolled plate with a grinded surface. The plates have excellent parallelism, are easy to machine and extremely dimensionally stable.

FINISHES

Thickness	grinded Ra1.6 (N7)
Tolerance	+0.2/0 mm
Protective film	one-sided
Cardboard	one-sided
Parallelism	≤0.1 mm
Evenness	≤0.2 mm
Length/width	Ra3.2-6.3 cut with a precision circular saw
HABA standard tolerance	nominal size +0.8/+0.3 mm
Customer-specific tolerance	within a tolerance field of 0.4 mm

We also produce other thicknesses and tolerances on request.

TECHNICAL SPECIFICATIONS

Tensile strength R_m	255-350 (N/mm ²)
Yield strength $R_{p0.2}$	≥105 (N/mm ²)
typical values	140-200 (N/mm ²)
Breaking strain ($L_o = 5 d_o$) A_5	≥12 %
typical values	17-22%
Brinell hardness (HBS)	≥ 70
Density	2.66 kg/dm ³
E-module	~70.000 N/mm ²
Thermal conductivity coefficient	110-140 W/mK
Thermal expansion coefficient	24.2 x 10 ⁻⁶ /K
Electrical conductivity	16-19 m/Ω mm ²
State	H111 (soft)

INSTRUCTIONS

HABA Alu35 is well suited for machining. Use tools for working aluminium with a cutting speed >2000 m/min. Threads are produced favourably with thread moulders.

CHEMICAL COMPOSITION

Magnesium	Mg	4.00-4.90 %	Copper	Cu	≤0.10 %
Manganese	Mn	0.40-1.00 %	Titanium	Ti	≤0.15 %
Chromium	Cr	0.05-0.25 %	Zinc	Zn	≤0.25 %
Iron	Fe	≤0.40 %	Other elements together		≤0.15 %
Silicium	Si	≤0.40 %	Other elements individually		≤0.05 %

DIN Material no.	3.3547
Designation	EN AW-5083 EN AW-AMg4.5Mn0.7
Material code	AMg4.5Mn
State	H111

MATERIAL IN USE

Plant and apparatus construction
Vehicle construction
Jig manufacturing
Prototype construction
Mechanical engineering
Toolmaking and mould construction
Ship and offshore construction
Low-temperature technology

APPLICATIONS

Base plates
Rotary tables
Side walls
Machined and engineered parts of all kinds
Foam and sample moulds

PROPERTIES

strength in the core	
of thicker plates	consistent
machinability	good
dimensional stability	very good
MIG/TIG weldability	good
Weatherproofness	excellent
Seawater resistance	excellent
Contact with foodstuffs	yes
tenacity	high
elongation	high

SURFACE TREATMENT

Decorative anodisation:	moderate
Protective anodisation:	excellent
Paintwork, coating:	good
Galvanic coating:	good
Chemical nickel coating:	excellent

All information is given to the best of our knowledge based on reasonable examination. However, like all technical application recommendations, they represent only non-binding information outside our contractual obligations, for which we accept no liability. In particular, they do not constitute any guarantee of properties and do not release the user from his own responsibility for checking the products supplied by us for their suitability for the intended purpose.

